Kynar® PVDF & FEP

Specifications

Temperature Range -40°F to +180°F

Vacuum Rating To 28" Hg

Diameter Tolerance ±.005"

Hardness

65 Shore D

Tube Markings None

Working Pressure 4:1 Safety Factor

Resin Compliance FDA, USPVI CFR 177.2600 UL 94 V0, NSF-51

Suggested Fittings Push-In, Compression

Kynar® PVDF

ynar® PVDF compound is an economical alternative to Teflon® (PTFE, PFA, and FEP) tubing for applications not requiring heat resistance. Kynar possesses excellent resistance to a wide range of chemicals. The high purity material is the ideal tubing for a variety of applications requiring an odorless and tasteless tube.

There are multiple grades of Kynar resins available. Some of these are used in rigid pipe applications. Freelin-Wade uses a flexible grade.

For more information about Kynar, refer to the Kynar Website: www.kynar.com You can also refer to our Chemical Resistance Chart on page 38.

Features

Resists:

- Acids
- Aromatics
- Halogen
- Radiation

Kynai

- Alcohol
- Mild Bases
- Fungus
- UV Light

- Aliphatics
- Chloride

• Resists fungal growth per MS 810B, Method 508 testing.

• Sterilizable by Gamma Radiation or Ozone.

Out-gassing







Temperature Range -100° F to +400° F -73° to 204° C

Vacuum Rating To 28" Hg

Diameter Tolerance ±.005"

Hardness

57 Shore D

Tube Markings

Working Pressure 4:1 Safety Factor

Resin Compliance

FDA Food Contact UL 94 VO, USP VI ASTM D 3296-03

Suggested Fittings Flare, Compression, Push-In

Fluorinated Ethylene Propylene - FEP

reelin-Wade's FEP tubing (compare to DuPont's® Teflon®) is one of the most durable and versatile flexible plastic tubes that you can buy. FEP, or fluorinated ethylene propylene, is an economical choice for applications requiring chemical resistance or exposure to a wide range of temperatures. Freelin-Wade's FEP is extremely flexible, making it an ideal choice for self-retracting coils. FEP is also available in a variety of packaged lengths.

Applications include chemical processing, laboratory applications, medical devices, water purification, food processing and automotive paint spray.

Features

- 100% virgin grade high performance resin designed to resist stress cracking
- Low permeability
- High thermal stability
- Non-flammable/Self-extinguishing
- · Superior electrical insulation properties
- Chemically inert to most industrial chemicals and solvents



| Part Number & Packaging Color Code Unit Size | OD | ID | Wall | Standard Colors | Working 75°F/25°C | Pressure 150°F/65°C | lbs./ 100' | Bend Radius | Fitting |
|---|----------|----------|------------|----------------------|----------------------|------------------------|---------------|-------------------------|---------|
| 1J-681 100' Bag 1C-681 500' Reel 1B-681 1000' Reel 1A-681 2500' Reel | 1/8" | 1/16" | .030" | 10 | 300 PSI | 125 PSI | 0.71 | 3/16" | PI, C |
| 1J-682 100' Bag 1B-682 500' Reel 1A-682 1000' Reel | 1/4" | .170" | .040" | 10 | 165 PSI | 70 PSI | 2.03 | 3/4" | PI, C |
| 1J-683 100' Bag 1A-683 500' Reel | 3/8" | 1/4" | .062" | ©0 | 165 PSI | 70 PSI | 4.72 | 1-1/4" | PI, C |
| 1J-684 100' Bag 1A-684 250' Reel 1AA-684 500' Reel | 1/2" | 3/8" | .062" | 10 | 130 PSI | 55 PSI | 6.61 | 2-1/8" Metric | • |
| Part Number & Packaging Color Code Unit Size | OD mm | ID mm | Wall mm | Standard Colors | | Pressure 150°F/65°C | lbs./ 100' | Bend Radius | Fitting |
| 1J-692 100' Bag 1B-692 500' Reel 1A-6921000' Reel | 6 | 4 | 1 | 10 | 195 PSI | 115 PSI | 1.88 | 15.9 mm | PI, C |
| 1J-693 100' Bag 1A-693 500' Reel | 8 | 6 | 1 | 10 | 145 PSI | 85 PSI | 2.63 | 49 mm | PI, C |
| 1J-695 100' Bag 1A-695 250' Reel | 12 | 10 | 1 | 10 | 90 PSI | 55 PSI | 4.07 | 98 mm | PI, C |
| Variations Available | : | | | Coiling • Colors • (| Cutting • | Printing • | Pack | aging • | Sizes |

Fluoringted Ethylene Propylene - FEP

| | | | | | riuorinate | ed Ethylene I | riopy | riene | - FEF |
|--|---|----------|----------|------------|-----------------|-------------------------------|---------------|----------------|---------|
| | Packaging Unit Size | OD | ID | Wall | Standard Colors | Working Pressure 75°F/25°C | lbs./ 100' | Bend Radius | Fitting |
| 1J-900 5 1C-900 5 1B-900 10 | 500' Reel 000' Reel | 1/8" | 1/16" | .030" | 10 | 300 PSI | 0.9 | 1/2" | PI, C |
| 1J-901 5 1B-901 5 1A-901 30 | 500' Reel | 1/4" | 3/16" | .030" | (10) | 150 PSI | 2.0 | 1" | PI, C |
| 1J-902 5 1B-902 5 1A-902 10 | 500' Reel | 1/4" | 1/8" | .062" | (10) | 300 PSI | 3.4 | 1/2" | PI, C |
| 1J-903 1A-903 10 | _ | 3/8" | 1/4" | .062" | (ii) | 207 PSI | 5.7 | 1" | PI, C |
| 1J-904 1A-904 10 | • | 1/2" | 3/8" | .062" | (10) | 155 PSI | 8.0 | 2" | PI, C |
| | | | | | | | | Metric | Sizes |
| Part Number & Color Code | Packaging Unit Size | OD mm | ID mm | Wall mm | Standard Colors | Working Pressure 75°F/25°C | lbs./ | Bend | Fitting |
| | | | | | | /3 F/Z3 C | 100' | Radius | riiiiig |
| 1J-941 1C-941 1 1B-941 1 1A-941 2 | 500' Reel 000' Reel | 4 | 2 | 1 | 10 | 450 PSI | | Radius | PI, C |
| 1C-941 1B-941 1 1A-941 2 1J-942 | 500' Reel 000' Reel 500' Reel 100' Bag 500' Reel | 4 | 2 | | (10) | | | | |
| 1C-941 1B-941 2 1J-942 1B-942 | 500' Reel 000' Reel 500' Reel 100' Bag 500' Reel 500' Reel 100' Bag | | | 1 | | 450 PSI | 1.4 | 1.5" | PI, C |
| 1C-941 1 1B-941 1 1A-941 2 1J-942 1B-942 2 1J-943 2 | 500' Reel 000' Reel 500' Reel 100' Bag 500' Reel 100' Bag 500' Reel 100' Bag | 6 | 4 | 1 | (10) | 450 PSI 350 PSI | 2.3 | 1.5" | PI, C |